

Electrafil® J-4/25/CF/15 NAT

Polyamide 612

Techmer Engineered Solutions

Message:

Electrafil® J-4/25/CF/15 NAT is a polyamide 612 (nylon 6/12) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The main features are: Rohs certification.

General Information			
RoHS Compliance	RoHS compliance		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	193	MPa	ASTM D638
Tensile Elongation (Break)	3.3	%	ASTM D638
Flexural Modulus	14100	MPa	ASTM D790
Flexural Strength	296	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	204	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.1E+3	ohms	ASTM D257
Volume Resistivity	55	ohms · cm	ASTM D257
Additional Information			

Surface Resistivity, Techmer Test Method: 100 to 10000 ohmVolume Resistivity, Techmer Test Method: 10 to 100 ohm-cm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT