

SUSTAPEEK GLD 140 FG blue

Polyetheretherketone

Röchling Sustaplast SE & Co. KG

Message:

- Product characteristics
- Excellent dimensional stability
- Very good sliding properties
- Meets the requirements of the regulation (EC) No. 1935/2004 on materials intended to come in contact with food
- Typical fields of application
- Food industry

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	Low Friction		
Uses	Non-specific Food Applications		
Agency Ratings	EC 1935/2004		
Appearance	Blue		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	86		ISO 868
Ball Indentation Hardness	220	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3700	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	150	°C	ISO 75-2/A
Continuous Use Temperature			
-- ¹	-30.0 to 250	°C	
-- ²	< 310	°C	
Melting Temperature	343	°C	ISO 11357-3
CLTE - Flow	5.5E-5	cm/cm/°C	DIN 53752
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	IEC 60093

Electric Strength	20	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		
NOTE			
1.	Long Term		
2.	Short Term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT