

4PROP® 9D13300

Polypropylene Homopolymer
4Plas

Message:

4PROP 9D13300 is a MFI 10 FR-V2 Homopolymer Polypropylene

General Information			
Features	Homopolymer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	25.0	MPa	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	8.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-2		UL 94
3.20 mm	V-2		UL 94
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	20.0 - 50.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	40.0 - 80.0	MPa	
Screw Speed	400	rpm	
Injection instructions			
Feed Throat Temperature: 20 - 60 °CBack Pressure: Low			
NOTE			
1.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

