

VESTAMID® D DX9321

Polyamide 612
Evonik Industries AG

Message:

Characterization: impact-resistant, 20% glass fiber reinforced, heat-stabilized
Applications: housings, coverings
Its advantages over PA 12 exhibit in the
heat deflection temperature (melting point nearly 40 °C higher)
tensile and flexural strength
outstanding recovery at high wet strength
The PA 612 compounds of the VESTAMID® D series consequently represent specialty products that complement the comprehensive selection of PA 12 compounds of the VESTAMID® L series.

General Information				
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Additive		Carbon Black		
		Heat Stabilizer		
Features		Food Contact Acceptable		
		Fuel Resistant		
		Good Abrasion Resistance		
		Grease Resistant		
		Heat Stabilized		
		High ESCR (Stress Crack Resist.)		
		High Impact Resistance		
		Light Stabilized		
		Oil Resistant		
		Solvent Resistant		
Uses		Housings		
Agency Ratings		FDA 21 CFR 177.1500		
Appearance		Black		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.19	1.19	g/cm³	ISO 1183
Molding Shrinkage ¹				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.70	--	%	
Water Absorption				ISO 62
Saturation, 23°C	2.0	--	%	
Equilibrium, 23°C, 50% RH	0.80	--	%	

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5700	4700	MPa	ISO 527-2/1A
Tensile Stress				ISO 527-2/1A
Yield	--	90.0	MPa	
Break	115	86.0	MPa	
Tensile Strain				ISO 527-2/1A
Yield	--	5.0	%	
Break	5.0	10	%	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C, Complete Break	11	11	kJ/m ²	
23°C, Complete Break	18	19	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C, Complete Break	110	100	kJ/m ²	
23°C, Complete Break	93	93	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	208	208	°C	ISO 75-2/B
1.8 MPa, Unannealed	189	189	°C	ISO 75-2/A
Vicat Softening Temperature	207	207	°C	ISO 306/B
Melting Temperature ²	215	215	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	7.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	5.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+14	--	ohms·cm	IEC 60093
Relative Permittivity				IEC 60250
100 Hz	4.40	--		
1 MHz	3.10	--		
Dissipation Factor				IEC 60250
100 Hz	0.050	--		
1 MHz	0.047	--		
Comparative Tracking Index				IEC 60112
Solution A ³	600	--	V	
Solution A ⁴	> 600	--	V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	HB		UL 94
Additional Information	Dry	Conditioned		Test Method
ISO Shortname	PA612-HI, MH, 14-050, GF20	--		ISO 1874

NOTE

1.	specimen 127x12.7x3.2 mm processing acc. to ISO 1874-2
2.	2nd Heating
3.	100 drops Value
4.	50 drops Value

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

