

4LAC® 25H20800

Acrylonitrile Butadiene Styrene
4Plas

Message:

4LAC 25H20800 is a Standard Flow Recycled ABS

General Information			
Features	Recyclable materials		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2600	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	43.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	15	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	108	°C	ISO 306/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	50.0 - 60.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	50.0 - 100	MPa	
Screw Speed	200	rpm	
Injection instructions			

Feed Throat Temperature: 30 - 50 °CBack Pressure: Low

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

