

POCAN® KU 2-7503/1 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, Extrusion, flame retardant

General Information			
UL YellowCard	E245249-474050		
Features	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.45	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 250°C, 2.00mm ¹	1.7	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.30	%	ISO 294-4
Flow direction: 250°C, 2.00mm ³	1.8	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.30	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.30	%	ISO 62

Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	130	MPa	ISO 2039-1

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2900	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	60.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	6.0	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	8.0	%	ISO 527-2/50
Tensile Creep Modulus			ISO 899-1
1 hr	2400	MPa	ISO 899-1
1000 hr	1400	MPa	ISO 899-1
Flexural Modulus ⁵ (23°C)	3000	MPa	ISO 178/A
Flexural Stress ⁶			
3.5% strain	90.0	MPa	ISO 178/A
23°C	100	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	6.0	%	
Electrolytical Corrosion	A1		IEC 60426

ISO Shortname	PBT, GFHMR, 11-030; ISO 1043-PBT FR (17)		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	100	kJ/m ²	ISO 179/1eU
23°C	130	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	90	kJ/m ²	ISO 180/1U
23°C	120	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Peak Force (23°C)	60.0	N	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	145	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	170	°C	ISO 306/B120
Ball Pressure Test (200°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	28	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.40		IEC 60250
23°C, 1 MHz	3.20		IEC 60250
Dissipation Factor			IEC 60250
23°C, 100 Hz	2.0E-3		IEC 60250
23°C, 1 MHz	0.016		IEC 60250
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.400 mm)	V-0		UL 94
Glow Wire Flammability Index (1.60 mm)	960	°C	IEC 60695-2-12

Glow Wire Ignition Temperature			IEC 60695-2-13
1.60 mm	700	°C	IEC 60695-2-13
3.00 mm	700	°C	IEC 60695-2-13

Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	240 - 260	°C	
Mold Temperature	80.0 - 100	°C	

NOTE	
1.	60x60x2; WZ 80°C; 600 Bar
2.	60x60x2
3.	60x60x2; WZ 80°C; 600 Bar
4.	60x60x2
5.	2.0 mm/min
6.	2.0 mm/min
7.	Pull Rate: 2 mm/min; 50% RH
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT