

KEBATER® PBT BF130

Polybutylene Terephthalate

BARLOG plastics GmbH

Message:

PBT, 30% glass fiber reinforced

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Resin ID (ISO 1043)	PBT-GF30		
Physical	Nominal Value	Unit	Test Method
Density	1.52	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.0	%	
Flow	0.40	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.15	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	145	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	12	kJ/m ²	
23°C	12	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	60	kJ/m ²	
23°C	60	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	4.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+19	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flammability Classification ² (0.800 mm)	HB		IEC 60695-11-10, -20

NOTE

- | | |
|----|---------------|
| 1. | 10°C/min |
| 2. | UL Registered |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

