

Ryton® BR111

Polyphenylene Sulfide

Solvay Specialty Polymers

Message:

Ryton® BR111 is a natural-colored glass fiber and mineral filled polyphenylene sulfide compound that provides enhanced mechanical strength with good electrical properties and outstanding chemical resistance, even at elevated temperatures.

General Information			
UL YellowCard	E54700-244869	E95746-102108298	
Filler / Reinforcement	Glass\Mineral		
Features	Good Chemical Resistance		
	Good Electrical Properties		
	Good Strength		
Uses	Automotive Applications		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.94	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.40	%	
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	101		
R-Scale	119		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	159	MPa	ASTM D638
--	165	MPa	ISO 527-2
Tensile Elongation (Break)	1.1	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	19300	MPa	ASTM D790
--	19000	MPa	ISO 178
Flexural Strength			
--	241	MPa	ASTM D790
--	255	MPa	ISO 178

Compressive Strength	295	MPa	ASTM D695
Poisson's Ratio	0.34		ISO 527
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
3.18 mm	75	J/m	ASTM D256
--	8.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	320	J/m	ASTM D4812
--	24	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.0E-5	cm/cm/°C	
Transverse : -50 to 50°C	3.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	7.0E-5	cm/cm/°C	
Thermal Conductivity	0.51	W/m/K	
UL Temperature Rating	220 to 240	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	4.70		
25°C, 1 MHz	4.60		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	3.0E-3		
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index (CTI)	225	V	UL 746
Insulation Resistance ¹ (90°C)	1.0E+10	ohms	
Flammability	Nominal Value	Unit	Test Method
	V-0		
Flame Rating (1.60 mm)	5VA		UL 94
Oxygen Index	65	%	ASTM D2863
NOTE			
1.	95%RH, 48 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

