

Propafilm™ RK140

Polypropylene Alloy

Innovia Films Ltd.

Message:

Heat Sealable Anti-Mist Coated Film

Biaxially oriented polypropylene (BOPP) film coated with two aqueous dispersions of polyvinylidene chloride (PVdC) copolymer.

RK100/120/140 are recommended for use as a single web in the salad industry. Particularly suited for medium to large packs on formfill-seal machines.

General Information			
Features	Antistatic		
	Excellent Printability		
	Food Contact Acceptable		
	Good Weather Resistance		
	Heat Sealable		
	High Gloss		
	Low Moisture Vapor Transmission		
Uses	Bi-axially Oriented Film		
	Food Packaging		
	Food Service Applications		
	Packaging		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			Internal Method
Flow : 121°C, 1 min	4.0	%	
Flow : 129°C, 1 min	7.0	%	
Across Flow : 129°C, 1 min	4.0	%	
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.25		
vs. Itself - Static	0.25		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	3600	µm	
Seal Strength ¹	0.15	N/mm	Internal Method
Seal Initiation Temperature ²	90.6 to 146	°C	Internal Method
Oxygen Permeability (25°C, 0% RH)	0.63	cm ³ · mm/m ² /atm/24 hr	ASTM F1927
Water Vapor Transmission Rate (38°C, 90% RH)	4.5	g/m ² /24 hr	ASTM F1770
Yield	29.1	m ² /kg	Internal Method
Optical	Nominal Value	Unit	Test Method

Gloss (45°)	100		ASTM D2457
Haze ³	3.0	%	ASTM D1003
NOTE			
1.	265°F; 1sec; 15lb/in ²		
2.	2secs; 15psi		
3.	Wide angle; 2.5°		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT