

AIE ABS 20G3F

Acrylonitrile Butadiene Styrene
Asia International Enterprise (Hong Kong) Limited

Message:

AIE ABS 20G3F is an Acrylonitrile Butadiene Styrene (ABS) material filled with 15% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.
Important attributes of AIE ABS 20G3F are:
Flame Rated
Flame Retardant
Rigid

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	High Rigidity		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Molding Shrinkage	0.20 to 0.40	%	Internal Method
Water Absorption (23°C, 24 hr)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	62.0	MPa	ISO 527-2
Tensile Strain (Break)	7.0	%	ISO 527-2
Flexural Modulus	4100	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	96.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	94.0	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (3.00 mm)	V-0	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

