

HiFill® TPX-HTN-01040 A

Polyamide
Techmer Engineered Solutions

Message:

HiFill® TPX-HTN-01040 A is a Polyamide product filled with 45% glass fiber. It can be processed by injection molding and is available in North America. Characteristics include:

Flame Rated
Heat Stabilizer
High Strength

General Information			
Filler / Reinforcement	Glass Fiber,45% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	High Temperature Strength		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.50	%	ASTM D955
Water Absorption (24 hr)	0.19	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	228	MPa	ASTM D638
Tensile Elongation (Break)	2.8	%	ASTM D638
Flexural Modulus	13100	MPa	ASTM D790
Flexural Strength	331	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	302	°C	ASTM D648
CLTE - Flow	3.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	24	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

