# neogol® 60 P UG

### Thermoplastic Polyolefin Elastomer

## API SpA

#### Message:

neogol®60 P UG is a polyolefin thermoplastic elastomer (TPO (POE)) product. It can be processed by co-extrusion molding or injection molding and is available in Europe.

Features include:

Copolymer

good weather resistance

General Information

| Features                                 | Block Copolymer  Good weather resistance |          |             |
|--|--|----------|-------------|
|  |  |          |             |
| Processing Method                        | Co-extrusion molding                     |          |             |
| ,  | Injection molding                        |          |             |
|  |  |          |             |
| Physical                                 | Nominal Value                            | Unit     | Test Method |
| Specific Gravity                         | 0.860                                    | g/cm³    | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (190°C/5.0 kg) | 140                                      | g/10 min | ASTM D1238  |
| Hardness                                 | Nominal Value                            | Unit     | Test Method |
| Durometer Hardness (Shore A, 15 sec)     | 60                                       |          | ASTM D2240  |
| Mechanical                               | Nominal Value                            | Unit     | Test Method |
| Tensile Strength                         |  |          | ASTM D638   |
|  | 5.00                                     | МРа      | ASTM D638   |
| 100% strain                              | 2.00                                     | МРа      | ASTM D638   |
| 300% strain                              | 2.70                                     | MPa      | ASTM D638   |
| Tensile Elongation (Break)               | 1100                                     | %        | ASTM D638   |
| Abrasion Resistance                      | 231                                      | mm³      | DIN 53516   |
| Elastomers                               | Nominal Value                            | Unit     | Test Method |
| Tear Strength <sup>1</sup>               | 29.0                                     | kN/m     | ASTM D624   |
| Compression Set                          |  |          | ASTM D395   |
| 23°C, 72 hr                              | 34                                       | %        | ASTM D395   |
| 70°C, 22 hr                              | 64                                       | %        | ASTM D395   |
| Injection                                | Nominal Value                            | Unit     |             |
| Rear Temperature                         | 155 - 175                                | °C       |             |
| Middle Temperature                       | 160 - 180                                | °C       |             |
| Front Temperature                        | 160 - 180                                | °C       |             |
| Nozzle Temperature                       | 165 - 190                                | °C       |             |
| Mold Temperature                         | 25 - 40                                  | °C       |             |
| Injection Rate                           | Moderate-Fast                            |          |             |

NOTE

1. With Notch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2