

Elexar® EL-3954-70

Thermoplastic Elastomer

Teknor Apex Company

Message:

Elexar® EL-3954-70 is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is extrusion or injection molding. Elexar® The main characteristics of the EL-3954-70 are: flame retardant/rated flame.

Typical application areas include:

Wire and cable

Electrical/electronic applications

General Information			
UL YellowCard	E54709-245343	E142591-100745019	
Uses	Underground cable		
	Cable sheath		
	Electrical wire sheath material		
	Electrical conductor insulation material		
	Wire and cable applications		
	Wire sheath		
	Industrial cable insulation material		
	Connector		
	cord sheath		
	Terminal cable sheath material		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.4	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.70	%	ASTM D955
Transverse flow	0.72	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.1	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	< -60.0	°C	ASTM D746
RTI Elec	90.0	°C	UL 746
RTI	90.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	42	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, All Colors)	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	199 - 216	°C	
Middle Temperature	213 - 221	°C	
Front Temperature	221 - 227	°C	
Nozzle Temperature	221 - 229	°C	
Processing (Melt) Temp	221 - 229	°C	
Mold Temperature	25.0 - 65.6	°C	
Injection Pressure	1.38 - 6.89	MPa	
Injection Rate	Moderate-Fast		
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 100	rpm	
Cushion	3.81 - 25.4	mm	
Injection instructions			
无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	193 - 210	°C	
Cylinder Zone 2 Temp.	199 - 216	°C	
Cylinder Zone 3 Temp.	213 - 221	°C	
Cylinder Zone 5 Temp.	221 - 227	°C	
Die Temperature	221 - 229	°C	
Extrusion instructions			
螺杆转速30 - 100 rpm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT