

EvoSource™ ABS 4535

Acrylonitrile Butadiene Styrene
MBA Polymers

Message:

A UL-HB recognized, easy flowing, post-consumer recycled acrylonitrile-butadiene-styrene copolymer for general use. Available in standard grey (reference 70/15) and standard black (reference 90/04).

General Information			
UL YellowCard	E226591-100590212		
Recycled Content	Yes		
Features	Copolymer		
	Good Flow		
Uses	General Purpose		
Appearance	Black		
	Grey		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	22	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2300	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	41.0	MPa	ISO 527-2/50
Flexural Modulus (23°C)	2250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	15	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	90.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
High Amp Arc Ignition (HAI) (1.50 to 2.80 mm)	PLC 1		UL 746
Hot-wire Ignition (HWI) ¹ (1.50 to 2.80 mm)	PLC 4		UL 746
Flammability	Nominal Value	Unit	Test Method

Flame Rating (1.50 to 2.80 mm)	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050 to 0.10	%
Processing (Melt) Temp	210 to 250	°C
Mold Temperature	40.0 to 60.0	°C
Extrusion	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050 to 0.10	%
Melt Temperature	200 to 220	°C
NOTE		
1.	ASTM D 3847	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT