

Kingfa API-1025

Polypropylene

Kingfa

Message:

PP-EPDM-T10

General Information			
Filler / Reinforcement	Talc filler, 10% filler by weight		
Additive	Rubber 2		
	UV stabilizer		
Features	Rigidity, high		
	Good UV resistance		
	High liquidity		
Uses	Car interior parts		
Appearance	Unspecified Color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960 - 1.00	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	23 - 28	g/10 min	ISO 1133
Molding Shrinkage (23°C)	0.012 - 0.013	%	Internal method
Ash Content ¹ (750°C)	10 - 13	%	ISO 3451
Weather Resistance ²	4.00 - 5.00		SAE J1960
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	24.0	MPa	ISO 527-2/50
Tensile Strain (Break)	25	%	ISO 527-2/50
Flexural Modulus ³	1700	MPa	ISO 178
Flexural Stress ⁴	34.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ⁵ (23°C)	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, unannealed, 4.00mm span)	115	°C	ISO 75-2/B
Flammability	Nominal Value		Test Method
Flame Rating ⁶	HB		ISO 3795
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	0.0 - 2.0	hr	
Rear Temperature	190 - 210	°C	

Middle Temperature	205 - 230	°C
Front Temperature	215 - 240	°C
Processing (Melt) Temp	220 - 245	°C
Mold Temperature	30.0 - 60.0	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.350	MPa

Injection instructions

Processing Temp. Limit: 250°C

NOTE

- | | |
|----|-----------------------|
| 1. | 30 min |
| 2. | 250 kJ/m ² |
| 3. | 2.0 mm/min |
| 4. | 2.0 mm/min |
| 5. | 4 mm |
| 6. | 360×100×3 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT