

Exxtral™ Performance Polyolefin CNU017

Polypropylene, Compounded (TPO)

ExxonMobil Chemical

Message:

A special thermoplastic polyolefin resin with high fluidity, high rigidity, low odor and low emission properties is generally suitable for automotive air conditioning devices.

General Information			
Features	Equilibrium rigidity/toughness		
	Impact resistance, good		
	Excellent appearance		
Uses	Parts under the hood of a car		
	Application in Automobile Field		
	Car interior parts		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.911	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	1800	MPa	ISO 527-2
Tensile Stress			ISO 527-2/50
Yield	31.0	MPa	ISO 527-2/50
Fracture	18.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	4.4	%	ISO 527-2/50
Fracture	35	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
0°C, complete fracture	3.5	kJ/m ²	ISO 179
23°C, complete fracture	5.7	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	105	°C	ISO 75-2/B
1.8 MPa, not annealed	56.0	°C	ISO 75-2/A

Legal statement

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用本产品不宜在与食品接触的应用中使用.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

