

Polyrocks 666(f1)

Polypropylene
Polyrocks Chemical Co., Ltd

Message:

666(f1) is flame retardant environmental polypropylene with bromine and antimony as the flame retardant elements. Through solid carbon, halogen-antimony synergistic mechanism play the flame retardant performance. 666(f1) flammability can reach UL 94 V-0, ultraviolet radiation reach f1 level (UL746C), relative temperature index (RTI) is 110°C (UL746B). 666(f1) has passed UL certification,and meet the requiements of RoHS, SVHC, PFOS & PFOA, 16P, PAHs...etc. 666(f1) has characteristics of high flame retardant, low density, non-dripping, good weatherability, strong chemical resistance, less corrosion to molds etc.

General Information			
Additive	Flame retardancy 2		
Features	Low density		
	Good chemical resistance		
	Good weather resistance		
	Halogen-free		
	Flame retardancy		
Uses	Lighting Applications		
	Electrical/Electronic Applications		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1000	MPa	ASTM D790
Flexural Strength	25.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	20	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
RTI Elec	110	°C	UL 746
RTI Imp	110	°C	UL 746
RTI	110	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			

0.75 mm	V-0	UL 94
--	SC-0	UL 1694

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

