

Jackdaw PLA HW10NT6624

Polylactic Acid
Jackdaw Polymers

Message:

Jackdaw PLA HW10NT6624 is a Polylactic Acid (PLA) product. It can be processed by extrusion and is available in Europe. Primary characteristic: eco-friendly/green.

General Information			
Features	Renewable Resource Content		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	35	g/10 min	ISO 1133
Molding Shrinkage	Internal Method		
Across Flow	0.40	%	
Flow	0.40	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800	MPa	ASTM D638, ISO 527-2
Tensile Stress			
Break	16.0	MPa	ISO 527-2
--	16.0	MPa	ASTM D638
Tensile Elongation (Break)	> 250	%	ASTM D638, ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	50.0	°C	ASTM D648, ISO 75-2/A
Melting Temperature	148	°C	ISO 1218, ASTM D2117

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT