

HiFill® POM CO 0374 S

Acetal (POM) Copolymer
Techmer Engineered Solutions

Message:
HiFill® POM CO 0374 S is an Acetal (POM) Copolymer product filled with metal. It can be processed by injection molding and is available in North America. Primary characteristic: copolymer.

General Information			
Filler / Reinforcement	Metal		
Features	Copolymer		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	3.73	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.6	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	41.4	MPa	ASTM D638
Tensile Elongation (Yield)	40	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	110	°C	
CLTE - Flow	2.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	1.0	hr	
Rear Temperature	177 to 193	°C	
Middle Temperature	188 to 210	°C	
Front Temperature	182 to 199	°C	

Nozzle Temperature	177 to 204	°C
Processing (Melt) Temp	193 to 216	°C
Mold Temperature	82.2 to 121	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

