Sylvin 4200-80UV Clear Grey 9541

Polyvinyl Chloride

Sylvin Technologies Incorporated

Message:

Sylvin 4200-80UV Grey 9541 Is A Vinyl Compound Formulated With A Non Ortho Phthalate Plasticizer For Molding Or Extrusion Applications That Require An Ultra Violet Stabilizer.

General Information			
Additive	Plasticizer		
	UV stabilizer		
Features	Non-phthalate plasticizer		
	General		
Uses	Industrial application		
	General		
Appearance	Grey		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	00		
SIIdW A	80		ASTM D2240
Shaw A, 10 seconds	80		ASTM D2240 ASTM D2240
		Unit	
Shaw A, 10 seconds	80	Unit MPa	ASTM D2240
Shaw A, 10 seconds Mechanical	80 Nominal Value		ASTM D2240 Test Method
Shaw A, 10 seconds Mechanical Tensile Strength (Break)	80 Nominal Value 15.9	МРа	ASTM D2240 Test Method ASTM D638
Shaw A, 10 seconds Mechanical Tensile Strength (Break) Tensile Elongation (Break)	80 Nominal Value 15.9 370	MPa %	ASTM D2240 Test Method ASTM D638 ASTM D638
Shaw A, 10 seconds Mechanical Tensile Strength (Break) Tensile Elongation (Break) Elastomers	80 Nominal Value 15.9 370 Nominal Value	MPa % Unit	ASTM D2240 Test Method ASTM D638 ASTM D638 Test Method
Shaw A, 10 seconds Mechanical Tensile Strength (Break) Tensile Elongation (Break) Elastomers Tear Strength	80Nominal Value15.9370Nominal Value70.1	MPa % Unit kN/m	ASTM D2240 Test Method ASTM D638 ASTM D638 Test Method ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

