

TOTAL Polypropylene Aceso® PPM R020

Polypropylene Random Copolymer

TOTAL Refining & Chemicals

Message:

Polypropylene PPM R020 is random copolymer polypropylene with a Melt Flow Index of 1.8 g/10 min specially developped for the extrusion blow-moulding of medical containers and medical devices, to the exclusion of implants.

General Information			
Uses	Containers		
	Medical/Healthcare Applications		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Extrusion Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.902	g/cm³	ISO 1183
Apparent Density	0.53	g/cm³	ISO 60
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.8	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ISO 527-2
Tensile Stress (Yield)	26.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m²	ISO 179
Notched Izod Impact Strength (23°C)	6.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	130	°C	ISO 306/A50
--	67.0	°C	ISO 306/B50
Melting Temperature (DSC)	149	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

