

NOVADURAN® 5505S

Polybutylene Terephthalate

Mitsubishi Engineering-Plastics Corp

Message:

NOVADURAN® 5505S is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific, Europe, or North America for extrusion or injection molding. Primary attribute of NOVADURAN® 5505S: Good Flexibility.

General Information	
UL YellowCard	E53664-101883220
Features	Good Flexibility
Forms	Pellets
Processing Method	Extrusion Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow : 2.00 mm	2.0	%	
Flow : 2.00 mm	2.2	%	
Water Absorption (Saturation, 23°C)	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ISO 527-2
Tensile Stress (Yield)	28.0	MPa	ISO 527-2
Tensile Strain (Yield)	19	%	ISO 527-2
Nominal Tensile Strain at Break	> 200	%	ISO 527-2
Flexural Modulus	740	MPa	ISO 178
Flexural Stress	31.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	145	°C	ISO 75-2/B
1.8 MPa, Unannealed	67.0	°C	ISO 75-2/A
Melting Temperature	222	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : -30 to 50°C	1.1E-4	cm/cm/°C	
Flow : -30 to 120°C	1.4E-4	cm/cm/°C	
Flow : 50 to 120°C	1.7E-4	cm/cm/°C	
Transverse : -30 to 50°C	9.0E-5	cm/cm/°C	

Transverse : -30 to 120°C	1.2E-4	cm/cm/°C	
Transverse : 50 to 120°C	1.5E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
1.00 mm	22	kV/mm	
2.00 mm	17	kV/mm	
Relative Permittivity (1 MHz)	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.020		IEC 60250
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	5.0 to 8.0	hr	
Rear Temperature	235	°C	
Middle Temperature	240	°C	
Front Temperature	250	°C	
Nozzle Temperature	245	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	20.0 to 150	MPa	
Screw Speed	80 to 150	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

