

Ecomass® 4703BI62

Polyurethane

Ecomass Technologies

Message:

Ecomass®4703BI62 is a polyurethane material that contains fillers. This product is available in North America and is processed by injection molding.

Ecomass®The main features of 4703BI62 are:

Good flexibility

non-toxic

General Information			
Filler / Reinforcement	Filler		
Features	Good flexibility		
	Non-toxic		
	Medium density		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.19	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.70 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	565	MPa	ASTM D638
Tensile Strength	20.7	MPa	ASTM D638
Tensile Elongation (Break)	230	%	ASTM D638
Flexural Modulus	145	MPa	ASTM D790
Flexural Strength	42.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	270	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	82.2	°C	
Drying Time - Desiccant Dryer	2.0	hr	
Drying Time, Maximum	4.0	hr	
Processing (Melt) Temp	204 - 221	°C	
Mold Temperature	10.0 - 26.7	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.103 - 0.172	MPa	
Screw Speed	100 - 250	rpm	
Clamp Tonnage	3.4 - 5.5	kN/cm ²	
Cushion	6.35 - 12.7	mm	
Screw L/D Ratio	20.0:1.0		
Screw Compression Ratio	2.5:1.0		

Injection instructions

Pack (Hold) Pressure: 65 to 75% of Injection Pressure Fill Time: 1.0 to 2.0 in/sec Pack (Hold) Time: 10 to 15 sec Cooling Time: As required Feed Throat:
Cooled Nozzle Type: Reverse Taper Check Type: Free Flow Dryer Dew Point: -20 to -40 °F Minimum Air Flow: 0.8 to 1.0 CFM Injection Pressure: As Required

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

