

INNOMID® CS 6-9830 HD

Polyamide 6 Alloy

Inno-Comp Ltd.

Message:

INNOMID ® CS 6-9830 HD is a 30 % glass-fibre-filled polyamide (PA-6) compound. This grade is available in nature and custom coloured form.

Recommended application

INNOMID ® CS 6-9830 HD is recommended for producing injection moulded products, where the required properties are high strength and stiffness.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Rigidity, high		
	High strength		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA-6 GF30		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.36	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	60.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ISO 527-2/2
Tensile Stress (Break)	130	MPa	ISO 527-2/1A/50
Flexural Modulus ¹	6600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	9.0	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	50	kJ/m ²	ISO 179/1eU
23°C	70	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	200	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (3.20 mm)	HB	UL 94	
Injection	Nominal Value	Unit	

Drying Temperature	60.0 - 80.0	°C
Suggested Max Moisture	0.10	%
Rear Temperature	220 - 260	°C
Middle Temperature	220 - 260	°C
Front Temperature	220 - 260	°C
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	60.0 - 100	°C
Injection Rate	Moderate	
Injection instructions		
Holding Pressure: 50-100% of actual injection pressure		
NOTE		

1. Type 1A, 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

