

NILAMID® A3 H CF40

Polyamide 66

Nilit Plastics

Message:

NILAMID® A3 H CF40 is a Polyamide 66 (Nylon 66) compound, 40% carbon fiber reinforced, heat stabilized.

This compound is intended for injection molding.

NILAMID® A3 H CF40 is primarily designed for the Automotive industry. It is also suitable for Industrial & Consumer applications.

General Information			
Filler / Reinforcement	Carbon Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Uses	Automotive Applications		
	Consumer Applications		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.30	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.40	%	
Flow : 23°C	0.20	%	
Water Absorption			ISO 62
23°C, 24 hr	0.60	%	
Saturation, 23°C	4.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	25000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	230	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	1.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	55	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	10	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	°C	ISO 75-2/A
Continuous Use Temperature ¹	130	°C	IEC 60216
Ball Pressure Test			
125°C	Pass		
165°C	Pass		

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ²	10	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+3	ohms·cm	IEC 60093
Comparative Tracking Index (3.20 mm, Solution A)	< 100	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		
Oxygen Index	28	%	ISO 4589-2
NOTE			
1.	20000 hr		
2.	23°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

