## ACCUCOMP™ ABS802L

## Acrylonitrile Butadiene Styrene

ACLO Compounders Inc.

## Message:

 $ACCUCOMP^{\text{\tiny TM}} \ ABS802L \ is \ an \ Acrylonitrile \ Butadiene \ Styrene \ (ABS) \ product. \ It \ is \ available \ in \ North \ America.$ 

Characteristics include:

Flame Rated

Impact Resistant

General Information			
Features	High Impact Resistance		
UL File Number	E56070		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.2	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1900	МРа	ASTM D638
Tensile Strength			ASTM D638
Yield	40.0	MPa	
Break	40.0	MPa	
Tensile Elongation			ASTM D638
Yield	3.0	%	
Break	25	%	
Flexural Modulus	2600	MPa	ASTM D790
Flexural Strength	63.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	440	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	87.0	°C	
1.8 MPa, Unannealed	77.0	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	НВ		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

