

Epocast 50-A1/946

Epoxy; Epoxide

Huntsman Advanced Materials

Message:

DESCRIPTION: Epocast® 50-A1 Resin/Hardener 946 epoxy laminating system is an unfilled, solvent-free, easy-to-handle material for the manufacture or repair of composite structures as well as for filament winding. Epocast® 50-A1 resin/Hardener 946 epoxy laminating system is self extinguishing. Epocast® 50-A1 / Hardener 946 is qualified to BMS 8-201, Type IV, Rev. F. This product is also available in a longer work life version - Epocast® 50-A1 resin/Hardener 9816 epoxy laminating system.

General Information			
Features	High strength		
	Fast curing		
	Self-extinguishing		
Uses	Laminate		
	Filament		
Appearance	Amber		
Forms	Liquid		
Processing Method	Filament power winding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
-- ¹	1.05	g/cm ³	ASTM D792
--	1.18	g/cm ³	ASTM D792
-- ²	1.21	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Compressive Modulus			ASTM D695
-- ³	23.6	MPa	ASTM D695
-- ⁴	25.2	MPa	ASTM D695
-- ⁵	27.9	MPa	ASTM D695
Compressive Strength			ASTM D695
-- ⁶	349	MPa	ASTM D695
-- ⁷	333	MPa	ASTM D695
-- ⁸	317	MPa	ASTM D695
Flammability	Nominal Value	Unit	Test Method
Flammability			FAR 25.853(a)
burn length		mm	FAR 25.853(a)
drip extinguishing time	0.0	hr	FAR 25.853(a)
self extinguishing time	0.0	hr	FAR 25.853(a)
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			

Resin	Mixing ratio by weight: 100		
Hardening method	Mixing ratio by weight: 15		
Thermoset Mix Viscosity	ASTM D2196		
25°C	2400	cP	ASTM D2196
25°C ⁹	400	cP	ASTM D2196
25°C ¹⁰	7770	cP	ASTM D2196

Additional Information

CURE SCHEDULE: Five days at 77°F (25°C) or two hours at 170-200°F (77-93°C) after room temperature gel. Handling and machining may be done after 8-16 hours at room temperature.

NOTE

1. Hardener
2. Resin
3. Cure 27 days at 77°F
4. Cure 1 day at 77°F + 2 hr. at 150°F
5. Cure 7 days at 77°F
6. Cure 27 days at 77°F
7. Cure 1 day at 77°F + 2 hr. at 150°F
8. Cure 7 days at 77°F
9. Hardener
10. Resin

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

