

LNP™ LUBRICOMP™ EFL36 compound

Polyether Imide

SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* EFL36 is a compound based on Polyetherimide resin containing 30% Glass Fiber, 15% PTFE. Added feature of this material is: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound EFL-4036

Product reorder name: EFL36

General Information			
UL YellowCard	E121562-101283889		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.62	g/cm³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.10 to 0.30	%	ASTM D955
Across Flow : 24 hr	0.40 to 0.60	%	ASTM D955
Flow : 24 hr	0.21 to 0.24	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.15	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.22	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	12700	MPa	ASTM D638
--	11200	MPa	ISO 527-2/1
Tensile Strength			
Break	176	MPa	ASTM D638
Break	168	MPa	ISO 527-2
Tensile Elongation (Break)	2.0	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	11300	MPa	ASTM D790
--	11400	MPa	ISO 178
Flexural Strength			
--	253	MPa	ASTM D790
--	249	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified

vs. Itself - Dynamic	0.46		
vs. Itself - Static	0.43		
Wear Factor - Washer	35.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	120	J/m	ASTM D256
23°C ²	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	710	J/m	ASTM D4812
23°C ³	47	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	10.3	J	ASTM D3763
--	3.65	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	202	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	204	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	4.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Transverse : -40 to 40°C	2.7E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	2.8E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	354 to 366	°C	
Front Temperature	366 to 377	°C	
Processing (Melt) Temp	360 to 366	°C	
Mold Temperature	121 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

