

Adell PP RP-18

Polypropylene Copolymer

Adell Plastics, Inc.

Message:

Adell PP RP-18 is a Polypropylene Copolymer (PP Copolymer) material filled with 40% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Water Absorption (24 hr)	0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	57		
R-Scale	105		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	51.7	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	4620	MPa	ASTM D790
Flexural Strength (Yield)	75.8	MPa	ASTM D790
Compressive Strength	47.6	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	124	°C	
1.8 MPa, Unannealed	116	°C	
Melting Temperature	149 to 171	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT