

NIMA HL 30530 GF FR

Polyethylene Terephthalate

Ovation Polymers Inc.

Message:

PET - Flame Retardant 30% Short Glass Fiber Reinforced.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6000	MPa	ASTM D638
Tensile Strength ² (Break)	115	MPa	ASTM D638
Tensile Elongation ³ (Break)	2.5	%	ASTM D638
Flexural Modulus ⁴	9000	MPa	ASTM D790
Flexural Strength ⁵ (Yield)	168	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	61	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	185	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating	V-0	UL 94	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

