

KEBAFORM® C 901 VT

Acetal (POM) Copolymer

BARLOG plastics GmbH

Message:

POM Copolymer unreinforced, antistatic

General Information			
Additive	Antistatic		
Features	Antistatic		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	2.0	%	
Flow	2.0	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	8.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	110	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

