

ULTEM™ 9085 resin

Polyether Imide

SABIC Innovative Plastics

Message:

High flow Polyetherimide blend. Meets FAR 25.853 and OSU 65/65 with low toxicity, smoke and flame evolution.

General Information	
Features	Low smoke
	Low toxicity
	High liquidity
Agency Ratings	FAR 25.853
	OSU 65/65
Processing Method	Profile extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (295°C/6.6 kg)	8.9	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (360°C/5.0 kg)	65.5	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.39	%	ISO 62
Equilibrium, 23°C, 50% RH	0.17	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3440	MPa	ASTM D638
--	3050	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	84.0	MPa	ASTM D638
Yield	88.0	MPa	ISO 527-2/5
Fracture ³	74.0	MPa	ASTM D638
Fracture	71.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.7	%	ISO 527-2/5
Fracture ⁵	72	%	ASTM D638
Fracture	50	%	ISO 527-2/5

Flexural Modulus			
50.0mm span ⁶	2920	MPa	ASTM D790
-- ⁷	2750	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0mm span ⁸	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	120	J/m	ASTM D256
23°C ⁹	13	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	153	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁰	152	°C	ISO 75-2/Af
Vicat Softening Temperature	173	°C	ISO 306/B120
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	49	%	ASTM D2863
FAA Flammability ¹¹			FAR 25.853
OSU peak heat release rate ¹²	36.0	kW/m ²	FAR 25.853
OSU total heat release ¹³	16.0	kW · min/m ²	FAR 25.853
Vertical Burn Test - Test a (60 s), passes at	2.0	sec	FAR 25.853
Injection	Nominal Value	Unit	
Drying Temperature	135	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	315 - 340	°C	
Middle Temperature	325 - 345	°C	
Front Temperature	330 - 350	°C	
Nozzle Temperature	330 - 350	°C	
Processing (Melt) Temp	330 - 350	°C	
Mold Temperature	120 - 150	°C	
Back Pressure	0.300 - 0.700	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	
Extrusion	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	80.0 - 100	°C	
Cylinder Zone 1 Temp.	265 - 275	°C	
Cylinder Zone 2 Temp.	280 - 295	°C	

Cylinder Zone 3 Temp.	290 - 305	°C
Cylinder Zone 4 Temp.	295 - 310	°C
Adapter Temperature	270 - 310	°C
Melt Temperature	280 - 310	°C
Die Temperature	260 - 310	°C
Calibration Temp, First	130 - 160	°C
Calibration Temp, Second	80.0 - 120	°C

NOTE

1.	5.0 mm/min
2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 5.0 mm/min
5.	Type 1, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4
10.	80*10*4 mm
11.	Method A/B
12.	5 minute test
13.	2 minute test

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT