

POLYFORT® FTP 3507

Compounded Polypropylene

A. Schulman Inc.

Message:

TPO 10% Talc

General Information			
Filler / Reinforcement	Talc,10% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	1.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.0	MPa	ISO 527-2/50
Flexural Modulus ²	1400	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	82.0	°C	ISO 75-2/B
Additional Information	Nominal Value	Unit	Test Method
Filler Content	10	%	ASTM D5630
NOTE			
1.	5x7 in plaque		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT