

DiaAlloy TC-30M

Polycarbonate
Mitsubishi Rayon America Inc.

Message:

DiaAlloy TC-30M is a Polycarbonate (PC) material. It is available in North America.
Important attributes of DiaAlloy TC-30M are:
Flame Rated
Heat Resistant
Impact Resistant
Typical application of DiaAlloy TC-30M: Automotive

General Information			
Features	High Heat Resistance		
	Low Temperature Impact Resistance		
Uses	Automotive Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.55	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	49.0	MPa	ASTM D638
Tensile Elongation (Yield)	90	%	ASTM D638
Flexural Modulus	2160	MPa	ASTM D790
Flexural Strength (Yield)	72.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	400	J/m	ASTM D256
Unnotched Izod Impact (23°C)	650	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	124	°C	
1.8 MPa, Unannealed	104	°C	
Melting Temperature	230 to 260	°C	
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT