

EPLAMID 66 MOS2 %2 GFR 30 NC

Polyamide 66

EPSAN Plastik SAN. ve TiC. A.S.

Message:

Polyamide 66, reinforced with 30% of glass fiber and molybdenum Disulfide 2% , heat stabilized, lubricated for injection moulding.
Eplamid 66 GFR 30 MOS2 %2 is used in all sectors of industry, offering a perfect balance of thermal and mechanical properties.
This product is available in natural and in black colours

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		Molybdenum disulfide lubricant (2%) heat stabilizer		
Features		Thermal Stability Lubrication		
Appearance		Black Natural color		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 3.00mm	0.80	--	%	ISO 294-4
Flow direction: 3.00mm	0.40	--	%	ISO 294-4
Moisture Content	0.20	--	%	ISO 15512
Ash Content	30	--	%	ISO 3451-4
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	87	--		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	12000	11500	MPa	ISO 527-2/50
Tensile Stress (Break, 23°C)	175	160	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	2.0	4.0	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	11300	11000	MPa	ISO 178
Flexural Stress ² (23°C)	255	230	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	11	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	9.0	11	kJ/m ²	ISO 180/1A

Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature (DSC)	255	--	°C	ISO 3146
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	HB	--		UL 94, IEC 60695-11-10, -20

Additional Information

干燥

TEST CONDITIONS: Laboratory conditions are 23 ±2°C and 45-55 % RH.

Injection	Dry	Unit
Drying Temperature	80.0	°C
Drying Time	2.0 - 4.0	hr
Processing (Melt) Temp	280	°C

NOTE

1. 2.0 mm/min
2. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT