

LNP™ LUBRILOY™ R2000 compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP LUBRILOY R2000 is a compound based on Nylon 66 resin containing Proprietary Lubricant. Added feature of this material is: Wear Resistant.
Also known as: LNP* LUBRILOY* Compound R
Product reorder name: R2000

General Information			
UL YellowCard	E121562-101344544		
Additive	Lubricant		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	1.8 to 2.2	%	
Across Flow : 24 hr	2.1 to 3.1	%	
Water Absorption (24 hr, 50% RH)	0.25	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2410	MPa	ASTM D638
Tensile Strength			
Yield	56.9	MPa	ASTM D638
Break	55.4	MPa	ASTM D638
Break	53.0	MPa	ISO 527-2
Tensile Elongation			
Yield	14	%	ASTM D638
Break	27	%	ASTM D638
Break	32	%	ISO 527-2
Flexural Modulus			
--	2320	MPa	ASTM D790
--	2000	MPa	ISO 178
Flexural Strength			
--	82.2	MPa	ASTM D790
--	65.0	MPa	ISO 178
Coefficient of Friction			
vs. Itself - Dynamic	0.36		
vs. Itself - Static	0.27		
Wear Factor - Washer	50.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	62	J/m	ASTM D256
23°C ²	6.7	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1700	J/m	ASTM D4812
23°C ³	140	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	77.8	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	85.0	°C	ISO 75-2/Af
CLTE			ASTM E831
Flow : -40 to 40°C	7.7E-5	cm/cm/°C	
Transverse : -40 to 40°C	1.0E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	271 to 282	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT