

Infino NH-1017SG

Polycarbonate + ABS

LOTTE ADVANCED MATERIALS CO., LTD.

Message:

Infino NH-1017SG is a polycarbonate acrylonitrile butadiene styrene (PC ABS) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: electrical/electronic applications.

Features include:

flame retardant/rated flame

Flame Retardant

General Information			
UL YellowCard	E115797-101069956		
Features	Flame retardancy		
Uses	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity (Natural)	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	48	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow: 3.20mm	0.29 - 0.36	%	ASTM D955
Transverse flow: 3.20mm	0.31 - 0.38	%	ASTM D955
Lateral flow: 3.20mm	0.31 - 0.38	%	ISO 2577
Traffic: 3.20mm	0.29 - 0.36	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2500	MPa	ASTM D638
--	2600	MPa	ISO 527-2/50
Tensile Strength			
Yield ²	64.0	MPa	ASTM D638
Yield	68.0	MPa	ISO 527-2/50
Fracture ³	52.0	MPa	ASTM D638
Fracture	50.0	MPa	ISO 527-2/50
Tensile Elongation			
Fracture ⁴	67	%	ASTM D638
Fracture	14	%	ISO 527-2/50
Flexural Modulus			
-- ⁵	2700	MPa	ASTM D790
-- ⁶	2900	MPa	ISO 178
Flexural Strength			
-- ⁷	94.0	MPa	ASTM D790

-- ⁸	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	6.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.18 mm	440	J/m	ASTM D256
23°C, 6.35 mm	140	J/m	ASTM D256
23°C ¹⁰	8.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 4.00mm	94.0	°C	ISO 75-2/B
0.45 MPa, annealing, 4.00mm	97.0	°C	ISO 75-2/B
1.8 MPa, unannealed, 6.40mm	84.0	°C	ASTM D648
1.8 MPa, not annealed, 4.00mm	84.0	°C	ISO 75-2/A
1.8 MPa, annealing, 4.00mm	91.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	100	°C	ISO 306/B50
--	103	°C	ISO 306/B120
Flammability	Nominal Value	Test Method	
Flame Rating (1.5 mm)	V-0	UL 94	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	50 mm/min		
5.	2.8 mm/min		
6.	2.0 mm/min		
7.	2.8 mm/min		
8.	2.0 mm/min		
9.	Thickness: 4mm		
10.	Thickness: 4mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT