

Monprene® OM-10160-01

Thermoplastic Elastomer

Teknor Apex Company

Message:

Monprene® OM-10160-01 is a Thermoplastic Elastomer (TPE) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Typical applications include:

- Handles
- Engineering/Industrial Parts
- Adhesives/Tapes
- Appliances
- Business/Office Goods

General Information			
Uses	Appliances		
	Bonding		
	Cell Phones		
	Dental Applications		
	Flexible Grips		
	Handles		
	Knobs		
	Overmolding		
	Power/Other Tools		
	Sporting Goods		
	Toothbrush Handles		
	Writing Instruments		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.928	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	7.58	MPa	ASTM D412
Tensile Strength (Break)	7.93	MPa	ASTM D412
Tensile Elongation (Break)	300	%	ASTM D412
Additional Information	Nominal Value		
Adhesion to Nylon			
Injection	Nominal Value	Unit	

Drying Temperature	65.6	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	232 to 243	°C
Middle Temperature	249 to 266	°C
Front Temperature	266 to 277	°C
Nozzle Temperature	271 to 288	°C
Processing (Melt) Temp	268 to 277	°C
Mold Temperature	23.9 to 60.0	°C
Injection Pressure	1.38 to 6.89	MPa
Injection Rate	Fast	
Back Pressure	0.172 to 0.862	MPa
Screw Speed	50 to 120	rpm
Cushion	3.81 to 25.4	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

