

LG ABS HG173

Acrylonitrile Butadiene Styrene

LG Chem Ltd.

Message:

LG ABS HG173 is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America, Latin America, Europe or Asia Pacific. The processing method is injection molding.
The main features of LG ABS HG173 are:
flame retardant/rated flame
high gloss
The typical application areas of LG ABS HG173 are: electrical/electronic applications

General Information			
UL YellowCard	E67171-248363		
Features	Highlight		
Uses	Electrical/Electronic Applications		
Processing Method	Injection molding		
Multi-Point Data	Specific Heat vs. Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.70	%	ASTM D955
Dimensional Stability	0.0	%	ASTM D1042
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2350	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	46.1	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	40	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2650	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	74.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	110	J/m	ASTM D256
-30°C, 6.40 mm	110	J/m	ASTM D256
23°C, 3.20 mm	250	J/m	ASTM D256
23°C, 6.40 mm	240	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	89.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	85.0	°C	ASTM D648
Vicat Softening Temperature	94.0	°C	ASTM D1525

RTI Elec			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746
RTI Imp			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746
RTI			UL 746
1.50 mm	60.0	°C	UL 746
3.00 mm	60.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	28	kV/mm	ASTM D149
Arc Resistance	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 0		UL 746
High Amp Arc Ignition (HAI)			UL 746
1.50 mm	PLC 2		UL 746
3.00 mm	PLC 0		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 1		UL 746
Hot-wire Ignition (HWI)			UL 746
1.50 mm	PLC 4		UL 746
3.00 mm	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm, ALL	HB		UL 94
3.00 mm, ALL	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	180 - 200	°C	
Middle Temperature	190 - 210	°C	
Front Temperature	200 - 220	°C	
Nozzle Temperature	200 - 230	°C	
Processing (Melt) Temp	210 - 240	°C	
Mold Temperature	40.0 - 70.0	°C	
Back Pressure	29.4 - 58.8	MPa	
Screw Speed	30 - 60	rpm	
Injection instructions			
Minimum Moisture Content: 0.01%			
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		

4.	15 mm/min
5.	15 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

