

# Petrothene® LR732001

High Density Polyethylene

LyondellBasell Industries

## Message:

Petrothene R732001 exhibits exceptional processability when used in a variety of different blowmolding processes. Finished articles made from this resin show an excellent balance of stiffness and environmental stress crack resistance. Typical applications include containers for bleach, detergent, household chemicals and personal care products.

General Information			
UL YellowCard	E62552-100622146		
Features	Food Contact Acceptable		
	Good Processability		
	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
Uses	Bottles		
	Containers		
	Profiles		
	Sheet		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Blow Molding		
	Profile Extrusion		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.953	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			
F50	> 500	hr	ASTM D2561
50°C, 100% Igepal CO-630, F50	30.0	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	67		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.6	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1250	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact	68.3	J/cm	ASTM D1822
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	75.0	°C	ASTM D648
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	126	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

