

LEXAN™ 920A resin

Polycarbonate

SABIC Innovative Plastics

Message:

Low viscosity injection moldable, flame retardant PC. Exceptional surface appearance. Clear, tints and opaque colors.

General Information			
UL YellowCard	E45587-236879	E207780-228406	
Additive	Flame retardancy		
Features	Excellent appearance		
	Flame retardancy		
Appearance	Opacity		
	Available colors		
	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.21	g/cm ³	ASTM D792
--	1.22	g/cm ³	ASTM D792
Specific Volume	0.835	cm ³ /g	ASTM D792
Radiant Panel Listing (UL)	YES		
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ASTM D570
24 hr	0.15	%	ASTM D570
Equilibrium, 23°C	0.35	%	ASTM D570
Equilibrium, 100°C	0.58	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	70		ASTM D785
Class r	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	62.1	MPa	ASTM D638
Fracture	55.8	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	7.0	%	ASTM D638
Fracture	90	%	ASTM D638

Flexural Modulus ³ (50.0 mm Span)	2240	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	91.0	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	640	J/m	ASTM D256
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D4812
Dart Drop Impact (23°C)	169	J	ASTM D3029
Tensile Impact Strength ⁵	525	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	138	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	132	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525 ⁶
CLTE - Flow (-40 to 95°C)	6.8E-5	cm/cm/°C	ASTM E831
Thermal Conductivity	0.19	W/m/K	ASTM C177
RTI Elec	130	°C	UL 746
RTI Imp	120	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Strength (3.20 mm, in Air)	17	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
50 Hz	3.01		ASTM D150
60 Hz	3.01		ASTM D150
1 MHz	2.96		ASTM D150
Dissipation Factor			ASTM D150
50 Hz	9.0E-4		ASTM D150
60 Hz	9.0E-4		ASTM D150
1 MHz	0.010		ASTM D150
Arc Resistance ⁷	PLC 7		ASTM D495
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 3		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.47 mm	V-2		UL 94
3.00 mm	V-0		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance (2540 µm)	85.0	%	ASTM D1003

Haze (2540 μm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	266 - 288	°C	
Middle Temperature	277 - 299	°C	
Front Temperature	288 - 310	°C	
Nozzle Temperature	282 - 304	°C	
Processing (Melt) Temp	288 - 310	°C	
Mold Temperature	71.1 - 93.3	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.025 - 0.076	mm	

NOTE

1. Type 1, 50mm/min
2. Type 1, 50mm/min
3. 1.3 mm/min
4. 1.3 mm/min
5. Type S
6. 标准 B (120°C/h), 载荷2 (50N)
7. Tungsten electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

