

Zytel® 151L NC010

NYLON RESIN
DuPont Performance Polymers

Message:
Unreinforced Polyamide 612

General Information				
UL YellowCard		E41938-234355		
Additive		Lubricant		
		Mold Release		
Features		Lubricated		
Agency Ratings		UL Unspecified Rating		
Forms		Pellets		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Shear Modulus vs. Temperature (ISO 11403-1)		
		Shear Stress vs. Shear Rate (ISO 11403-1)		
		Tensile Modulus vs. Temperature, Dynamic (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)		>PA612<		
Resin ID (ISO 1043)		PA612		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.06	--	g/cm ³	ISO 1183
Molding Shrinkage				
Flow : 3.20 mm	1.1	--	%	Internal Method
Across Flow : 3.20 mm	1.1	--	%	Internal Method
Across Flow	1.4	--	%	ISO 294-4
Flow	1.3	--	%	ISO 294-4
Water Absorption				ISO 62
23°C, 24 hr, 2.00 mm	3.0	--	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	1.3	--	%	
Viscosity Number (96% H2SO4 (Sulphuric Acid))	95.0	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	114	--		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method

Tensile Modulus	2400	1700	MPa	ISO 527-2
Tensile Stress (Yield)	62.0	54.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.5	18	%	ISO 527-2
Nominal Tensile Strain at Break	17	> 50	%	ISO 527-2
Flexural Modulus	2100	1440	MPa	ISO 178
Films	Dry	Conditioned	Unit	Test Method
Tensile Elongation - MD (Yield)	4.5	--	%	ISO 527-3
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	3.5	3.0	kJ/m ²	
23°C	3.5	4.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	40 kJ/m ²		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180/1A
-30°C	4.5	3.0	kJ/m ²	
23°C	4.0	4.5	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	135	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	62.0	--	°C	ISO 75-2/A
Glass Transition Temperature ¹	65.0	35.0	°C	ISO 11357-2
Vicat Softening Temperature	181	--	°C	ISO 306/B50
Melting Temperature ²	218	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.1E-4	--	cm/cm/°C	
Flow : -40 to 23°C	9.0E-5	--	cm/cm/°C	
Flow : 55 to 160°C	1.6E-4	--	cm/cm/°C	
Transverse	1.2E-4	--	cm/cm/°C	
Transverse : -40 to 23°C	9.0E-5	--	cm/cm/°C	
Transverse : 55 to 160°C	1.8E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms · cm	IEC 60093
Electric Strength	30	30	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.60	5.10		

1 MHz	3.20	4.00		
Dissipation Factor				IEC 60250
100 Hz	0.014	0.070		
1 MHz	0.016	0.040		
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.850 mm	V-2	--		
1.50 mm	V-2	--		
Oxygen Index	27	--	%	ISO 4589-2
Fill Analysis	Dry	Conditioned	Unit	Test Method
Melt Density	0.900	--	g/cm ³	
Specific Heat Capacity of Melt	2750	--	J/kg/°C	
Thermal Conductivity of Melt	0.18	--	W/m/K	
Emission of Organic Compounds	3.10	--	µgC/g	VDA 277
NOTE				
1.	10°C/min			
2.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

