megol® SAT 90

Styrene Ethylene Butylene Styrene Block Copolymer API SpA

Message:

megol® SAT 90 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Europe.

Characteristics include:

Chemical Resistant

Eco-Friendly/Green

Fast Molding Cycle

Food Contact Acceptable

Good Processability

General Information													
Features	Acid Resistant												
	Base Resistant												
	Detergent Resistant Fast Molding Cycle Food Contact Acceptable Good Chemical Resistance												
						Good Processability Good UV Resistance Good Weather Resistance High Flow High Heat Resistance Low Temperature Resistant							
											Ozone Resistant		
											Recyclable Material		
	Processing Method	Injection Molding											
	Physical	Nominal Value	Unit	Test Method									
	Specific Gravity	0.980	g/cm³	ASTM D792									
	Hardness	Nominal Value	Unit	Test Method									
	Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240									
	Mechanical	Nominal Value	Unit	Test Method									
Tensile Strength			ASTM D638										
	10.0	MPa											
100% Strain	6.20	MPa											
300% Strain	7.20	MPa											
Tensile Elongation (Break)	600	%	ASTM D638										
Elastomers	Nominal Value	Unit	Test Method										
Tear Strength ¹	48.0	kN/m	ASTM D624										

Compression Set			ASTM D395
70°C, 24 hr	62	%	
100°C, 24 hr	80	%	
Additional Information	Nominal Value		
Ozone Resistance ² (40°C)	Excellent		
NOTE			
1.	Without Notch		
2.	72 hr, 200 ppcm, Tension=20%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

