

HiFill® PES GF10

Polyethersulfone

Techmer Engineered Solutions

Message:

HiFill® PES GF10 is a Polyethersulfone (PESU) product filled with 10% glass fiber. It can be processed by injection molding and is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (24 hr)	0.18	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	114	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	4140	MPa	ASTM D790
Flexural Strength	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	207	°C	ASTM D648
CLTE - Flow	5.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹	22	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	143	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	343 to 391	°C	
Middle Temperature	343 to 391	°C	
Front Temperature	343 to 391	°C	
Processing (Melt) Temp	332 to 388	°C	
Mold Temperature	138 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	

Screw Speed	50 to 100	rpm
-------------	-----------	-----

NOTE

- | | |
|----|-----------------------|
| 1. | Method A (Short-Time) |
|----|-----------------------|

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material
--

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT