

Akulon® K224-LGM35

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® K224-LGM35 is a Polyamide 6 (Nylon 6) material filled with 15% glass fiber and 25% mineral. It is available in Asia Pacific or North America. Important attributes of Akulon® K224-LGM35 are:
Good UV Resistance
UV Stabilized
Typical application of Akulon® K224-LGM35: Automotive

General Information				
Filler / Reinforcement		Glass Fiber,15% Filler by Weight Mineral,25% Filler by Weight		
Additive		UV Stabilizer		
Features		Good UV Resistance		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.49	--	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	1.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9000	4800	MPa	ISO 527-2
Tensile Stress (Break)	120	67.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2
Flexural Modulus	7700	--	MPa	ISO 178
Flexural Stress	165	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	3.0	kJ/m ²	
23°C	5.0	6.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	25	--	kJ/m ²	
23°C	30	--	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
Melting Temperature ¹	220	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.8E-5	--	cm/cm/°C	

Transverse	1.0E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	1.0E+12	ohms·cm	IEC 60093
Electric Strength	35	30	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.50	14.0		
1 MHz	3.30	4.50		
Dissipation Factor				IEC 60250
100 Hz	5.0E-3	0.32		
1 MHz	0.014	0.12		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	255 to 265		°C	
Middle Temperature	265 to 275		°C	
Front Temperature	265 to 280		°C	
Nozzle Temperature	260 to 280		°C	
Processing (Melt) Temp	250 to 285		°C	
Mold Temperature	50.0 to 80.0		°C	
Injection Rate	Moderate-Fast			
Back Pressure	3.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

