

LNP™ THERMOCOMP™ LF005 compound

Polyetheretherketone

SABIC Innovative Plastics

Message:

LNP THERMOCOMP LF005 is a compound based on Polyetheretherketone resin containing 25% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound LF-1005

Product reorder name: LF005

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.50 to 0.70	%	ASTM D955
Across Flow : 24 hr	1.0 to 1.2	%	ASTM D955
Across Flow : 24 hr	1.1	%	ISO 294-4
Flow : 24 hr	0.64	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	11700	MPa	ASTM D638
--	11400	MPa	ISO 527-2/1
Tensile Strength			
Yield	157	MPa	ASTM D638
Yield	158	MPa	ISO 527-2
Break	157	MPa	ASTM D638
Break	158	MPa	ISO 527-2
Tensile Elongation			
Yield	2.7	%	ASTM D638, ISO 527-2
Break	2.7	%	
Flexural Modulus			
--	8960	MPa	ASTM D790
--	8600	MPa	ISO 178
Flexural Strength			
--	248	MPa	ASTM D790
--	243	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	91	J/m	ASTM D256
23°C ²	8.9	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	930	J/m	ASTM D4812
23°C ³	60	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	14.6	J	ASTM D3763
--	3.50	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed, 64.0 mm Span)	239	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	5.4E-6	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	5.2E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	1.8E-6	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	1.9E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Rear Temperature	370 to 380	°C	
Middle Temperature	380 to 400	°C	
Front Temperature	380 to 400	°C	
Mold Temperature	175 to 190	°C	
Back Pressure	0.300 to 0.700	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

