

XYRON™ G702H

Polyphenylene Ether + PS
Asahi Kasei Chemicals Corporation

Message:
Modified PPE
20% Filler reinforced Non-Flame retardant

General Information			
UL YellowCard	E82268-250831		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Molding Shrinkage ¹ (2.00 mm)	0.25 to 0.50	%	Internal Method
Water Absorption (23°C, 24 hr)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	102	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2
Flexural Modulus (23°C)	5870	MPa	ISO 178
Flexural Stress (23°C)	162	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	11	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	140	°C	ASTM D648
1.8 MPa, Unannealed	139	°C	ISO 75-2/A
CLTE - Flow (-30 to 65°C)	5.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms · cm	IEC 60093
Electric Strength ³ (2.00 mm)	43	kV/mm	IEC 60243-1
Dielectric Constant			IEC 60250
100 Hz	3.10		
1 MHz	3.10		
Dissipation Factor			IEC 60250
100 Hz	6.0E-4		
1 MHz	1.1E-3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	90.0 to 100	°C
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	260 to 300	°C
Mold Temperature	60.0 to 100	°C

NOTE		
1.	150x150x2 mm	
2.	4 mm	
3.	Short Time	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

