

DINALON® A1X25 V0

Polyamide 66

Grupo Repol

Message:

DINALON® A1X25 V0 is a Polyamide 66 (Nylon 66) product. It is available in Europe.

Characteristics include:

Flame Rated

Halogen Free

General Information			
Features	Halogen Free		
	Low (to None) Phosphorus Content		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm³	ISO 1183/A
Humidity ¹	< 0.25	%	ISO 15512/B
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3800	MPa	ISO 527-2
Tensile Stress (Break)	75.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	3300	MPa	ISO 178
Flexural Stress	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.5	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306/B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
NOTE			
1.	Karl-Fischer		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

