

TECHNYL® B 218L V30 BLACK 44 N

Polyamide 66/6 Copolymer
Solvay Engineering Plastics

Message:
Copolyamide 66/6, reinforced with 30% of glass fibre, for injection moulding, heat stabilized with improved UV ageing resistance.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Surface Finish		
		Good UV Resistance		
		Heat Stabilized		
Uses		Automotive Applications		
		Handles		
		Housings		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66/6-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	0.70	--	%	
Flow	0.50	--	%	
Water Absorption (23°C, 24 hr)	0.95	--	%	ISO 62
Molding Shrinkage Isotropy	0.710	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9800	5900	MPa	ISO 527-2/1A
Tensile Stress (Break)	185	115	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.0	8.0	%	ISO 527-2/1A
Flexural Modulus	8300	4700	MPa	ISO 178
Flexural Stress	230	140	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	11	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	80	92	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	11	19	kJ/m ²	ISO 180/1A

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	230	--	°C	ISO 75-2/Af
Melting Temperature	242	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	2.6E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	3.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	35	34	kV/mm	IEC 60243-1
Relative Permittivity	3.70	--		IEC 60250
Dissipation Factor	0.010	--		IEC 60250
Comparative Tracking Index (Solution A)	450	325	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	250 to 270		°C	
Middle Temperature	260 to 270		°C	
Front Temperature	270 to 280		°C	
Mold Temperature	80.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT