

Bergamid™ A70 white

Polyamide 66
PolyOne Corporation

Message:

Bergamid™ A70 white is a Polyamide 66 (Nylon 66) product. It is available in Africa & Middle East, Asia Pacific, or Europe. Primary characteristic: rohs compliant.

General Information			
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.13	g/cm ³	DIN 53479
K-Value ²	74.0 to 78.0		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1600	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	60.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	25	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.4	kJ/m ²	
23°C	53	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
Maximum Use Temperature			IEC 60216
-- ³	100	°C	
Short Time	200	°C	
Melting Temperature (DSC)	261	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+12	ohms · cm	IEC 60093
Electric Strength	80	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	5.00		IEC 60250
Dissipation Factor (1 MHz)	0.20		IEC 60250
Comparative Tracking Index (Solution A)	600	V	IEC 60112
NOTE			

1.	$\pm 0.03 \text{ g/cm}^3$
2.	96% H ₂ SO ₄
3.	Continuous (GTP 50% Tensile)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

